

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problems Mailbox.**

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 297/08	A1	(11) International Publication Number: WO 97/40080 (43) International Publication Date: 30 October 1997 (30.10.97)
(21) International Application Number: PCT/FI97/00240 (22) International Filing Date: 18 April 1997 (18.04.97) (30) Priority Data: 961722 19 April 1996 (19.04.96) FI (71) Applicant (for all designated States except US): BOREALIS A/S [DK/DK]; Lyngby Hovedgade 96, DK-2800 Lyngby (DK). (72) Inventors; and (75) Inventors/Applicants (for US only): HÄRKÖNEN, Mika [FI/FI]; Vanha Myllypolku 18 C, FIN-01360 Vantaa (FI). MALM, Bo [FI/FI]; Harjuviita 16 A 27, FIN-02110 Espoo (FI). NYMARK, Anders [FI/FI]; Kahdeksantoistamäenkuja 5, FIN-06100 Porvoo (FI). (74) Agent: BERGGREN OY AB; P.O. Box 16, FIN-00101 Helsinki (FI).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>

(54) Title: PROCESS FOR THE PREPARATION OF CREEP-RESISTANT POLYPROPYLENE BLOCK COPOLYMERS**(57) Abstract**

The invention relates to a process for the preparation of a polypropylene for e.g. pipe applications, containing from 1.0 to 10.0 % by weight of ethylene or C₄-C₁₀- α -olefin repeating units and having an MFR₂ value of between 0.05 and 0.40 g/10 min by polymerizing propylene and ethylene in the presence of a catalyst system. The creep-resistance of the polypropylene is improved by performing the process by means of the following steps: (a) copolymerizing propylene and ethylene into a random copolymer at 40 to 110 °C using: a portion of ethylene or C₄-C₁₀- α -olefin leading to 1.0 to 10.0 % by weight of ethylene repeating units in said random copolymer; and no or a minimal amount of hydrogen leading to an MFR₁₀ value of between 0.01 and 5.0 g/10 min for said random copolymer, if this step is performed first, or to an MFR₂ value for said polypropylene of between 0.05 and 0.40 g/10 min, if this step is performed after step (b); the proportion of random copolymer of this step being from 20 to 80 % by weight of said polypropylene, (b) polymerizing propylene at 40 to 110 °C using: no or a minimal portion of ethylene leading to 0.0 to 1.0 % by weight of ethylene repeating units in the polymer resulting from this step; and an amount of hydrogen leading to an MFR₂ value for said polypropylene of between 0.05 and 0.40 g/10 min, if this step is performed after step (a); the proportion of polymer of this step being from 80 to 20 % by weight of said polypropylene. The polypropylene can be elastomer modified.

PROCESS FOR THE PREPARATION OF CREEP-RESISTANT POLYPROPYLENE BLOCK COPOLYMERS

The invention relates to a process for the preparation of rigid polypropylene for e.g. pipe, fiber, profile and moulding applications, containing from 1.0 to 10.0% by weight of ethylene repeating units and having a MFR₂ value of between 0.05 and 0.40 g/10 min, by polymerizing propylene and ethylene or a C₄-C₁₀- α -olefin in the presence of a catalyst system, the procatalyst component of which is a reaction product of at least a tetravalent titanium compound and a magnesium halide compound and the cocatalyst component of which comprises an organoaluminium compound, and hydrogen as a molecular weight regulating agent, to give said polypropylene.

The invention also relates to a process for the preparation of elastomer modified polypropylene for e.g. pipe, fiber, profile and moulding applications, containing from 1.0 to 30% by weight of ethylene or a C₄-C₁₀- α -olefin repeating units and having a MFR₂ value of between 0.05 and 50 g/10 min, by polymerizing propylene and ethylene or a C₄-C₁₀- α -olefin in the presence of a catalyst system, the procatalyst component of which is a reaction product of at least a tetravalent titanium compound and a magnesium halide compound and the cocatalyst component of which comprises an organoaluminium compound, and hydrogen as a molecular weight regulating agent, as well as providing an elastomer component, to give said elastomer modified polypropylene.

Finally, the invention also relates to a creep-resistant polypropylene made by the above processes and its use.

By Melt Flow Rate (MFR) is meant the weight of a polymer extruded through a standard cylindrical die at a standard temperature in a laboratory rheometer carrying a standard piston and load. Thus MFR is a measure of the melt viscosity of a polymer and hence also of its molecular weight. The smaller the MFR, the larger is the molecular weight. It is frequently used for characterizing a polyolefins, e.g. polypropylene, where the standard conditions MFR_{mi} are: temperature 230°C; die dimensions 9.00 mm in length and 2.095 mm in diameter; load of the piston, 2.16 kg (mi=2), 5.0 kg (mi=5), 10.0 kg (mi=10), 21.6 kg (mi=21). See Alger, M.S.M., Polymer Science Dictionary, Elsevier 1990, p. 257. The standard generally used are ISO 1133 C4, ASTM D 1238 and DIN 53735.

By Flow Rate Ratio (FRR) is meant the ratio between the Melt Flow Rate (MFR) measured at a standard temperature and with standard die dimensions using a heavy load and the melt flow rate measured at the same temperature with the same die dimensions using a light load. Usually, for propylene polymers are used nominal loads 10.0 kg and 2.16 kg (ISO 1133 C4). The larger the value of the FRR, the broader the molecular weight distribution.

Polypropylene copolymer has many characteristics which makes it desirable for applications like pipes, fittings, moulded articles, foams etc. Polypropylene as piping material is mainly used in non-pressure applications (pipe and fittings) and profiles. There is a small volume used for pressure pipe, mainly hot water and industrial pipes. The good thermal resistance of polypropylene compared to other polyolefins is utilized for the pipe applications. All three main types of propylene polymer, i.e. homopolymers, random copolymers and block copolymers are used. Homopolymers give the pipe good rigidity but the impact and creep properties are not very good. The block copolymers give good impact properties but the creep properties are like homopolymers due to the homopolymer matrix. Propylene ethylene random copolymers are used for pressure pipe applications for hot water and industrial pipes.

The propylene-ethylene random copolymers for pressure pipes are today produced with high yield Ziegler-Natta catalysts in processes (bulk or gas phase) giving a material having a relatively narrow molecular weight distribution ($MWD = M_w/M_n$) of about 5, corresponding to a FRR (MFR_{10}/MFR_2) of 13-17. The molecular weight (M_w) of the pipe material with melt flow rate (MFR_2) of 0.1-0.4 is about 600 000 - 1 000 000. This high molecular weight and the narrow MWD cause problems in compounding and extrusion of pipes. The processability of such materials is difficult due to the low shear sensitivity causing unwanted degradation of the material and melt fracture, which is seen as uneven surface and thickness variations of the pipes. In addition the conventional propylene random copolymer pipe materials produced in one phase have not strength enough for the short and long term properties (notch resistance and creep) needed for good pressure pipes.

The processability of the conventional propylene random copolymers can be improved by broadening the MWD using multi-stage polymerization processes. In multi-stage polymerization the MWD of the polymer can be broadened by producing different molecular weight polymers in each stage. The MWD of polymer becomes broader when lower molecular weight polymer is reactor-blended into the higher molecular weight polymer adjusting the final MFR by choosing the right

molecular weight and the reactor split in each stage. The molecular weight of the polymer in each step can be controlled by hydrogen which acts as a chain transfer agent. Reactor temperature may be also used for controlling the molecular weight of polymer in each step. Multi-stage polymerization is disclosed e.g. in patent application JP-91048, but the process concerns film grade polypropylene with a final MFR₂ of about 1.5.

When the processability is improved by producing broader MWD propylene random copolymer, also the amount of low molecular fraction is increased if the comonomer feeds are the same in each stage. The taste and odour are adversely affected.

- 10 By using a concept invented with high yield TiCl_4 catalyst it is possible to produce pipe material having improved mechanical and pipe properties and also a good extrudability. The improved strength properties of the material come from a very high molecular weight fraction of $M_w \geq 2\,000\,000$ g/mol and totally novel comonomer distribution together with a broad molecular weight distribution. In
- 15 another embodiment of the invention, an elastomer is provided within this propylene product for increased impact strength.

The embodiment of the invention relating to a non-elastomeric polypropylene product is essentially characterized by what is said in the characterizing part of claim 1. Thus the invented concept is based on the idea of producing a broad MWD

20 and a high molecular weight propylene random copolymer and improved comonomer distribution using high yield catalysts in two or several reactors at different reaction conditions. The comonomers incorporated in long chains as described in this invention destroy the regularity of the chains leading to the more homogenous distribution of the essential tie-chains and entanglements needed for

25 creep properties and toughness in pipe materials.

The low molecular weight fraction contains no or minimal portion of ethylene repeating units in the polymer. Together with the high molecular weight random copolymer fraction this fraction is improving the processability. The no or low ethylene content fraction gives the total polymer the stiffness needed for rigid

30 materials e.g. pipes, profiles and moulding applications.

A homopolymer or a minirandom copolymer (ethylene < 1%) is known to have a stiffness of 1400-1700 MPa when a random copolymer with an ethylene content of $\geq 2\%$ has a stiffness of < 1000 MPa.

The problem with the uneven comonomer distribution with high yield TiCl_4 catalysts is solved in a way that the amount of comonomer is split between the reactors. To the reactor where the high molecular weight propylene polymer is produced is fed more essentially all, comonomer compared to the reactor where the low molecular PP is produced. Higher amounts of comonomer can be fed because the solubility of the high molecular weight polymer is lower. The final comonomer content is adjusted by controlling the comonomer feed into the reactor. The intervals given in this publication always include both limits thereof.

Thus one embodiment of the present invention relates to a process for the preparation of polypropylene for e.g. pipe, fiber, profile and moulding applications. Such a grade of polypropylene has from 1.0 to 10.0% by weight of ethylene or a $\text{C}_4\text{-C}_{10}\text{-}\alpha\text{-olefin}$ repeating units and has a MFR_2 value of between 0.10 and 0.40 g/10 min. The preparation takes place by polymerizing propylene and ethylene or a $\text{C}_4\text{-C}_{10}\text{-}\alpha\text{-olefin}$ in the presence of a catalyst system, the procatalyst component of which is a reaction product of at least a tetravalent titanium compound and a magnesium halide compound, and a cocatalyst component of which comprises an organoaluminium compound, optionally an external electron donor and hydrogen as a molecular weight regulating agent.

It has been found that extremely creep-resistant polypropylene can be prepared by applying the following steps in any mutual order:

- (a) copolymerizing propylene and ethylene or a $\text{C}_4\text{-C}_{10}\text{-}\alpha\text{-olefin}$ into a random copolymer at 40 to 110°C using: a catalyst system of the above-mentioned type; a portion of ethylene or $\text{C}_4\text{-C}_{10}\text{-}\alpha\text{-olefin}$ leading to 1.0 to 10.0% by weight of ethylene or $\text{C}_4\text{-C}_{10}\text{-}\alpha\text{-olefin}$ repeating units in said random copolymer; and no or a minimal amount of hydrogen leading to a MFR_{10} value of between 0.01 and 5.0 g/10 min for said random copolymer, if this step is performed first, or to a MFR_2 value for said polypropylene of between 0.05 and 0.40 g/10 min, if this step is performed after step (b); the proportion of random copolymer of this step being from 20 to 80% by weight of said polypropylene,
- (b) polymerizing propylene at 40 to 110°C using: a catalyst system of the above-mentioned type; no or a minimal portion of ethylene leading to 0.0 to 1.0% by weight of ethylene repeating units in the polymer resulting from this step; and an amount of hydrogen leading to a MFR_2 value of between 20 and 1000 g/10 min for said polymer, if this step is performed first, or to a MFR_2 value for said polypropylene of between 0.05 and 0.40 g/10 min, if this step is performed after step (a);

the proportion of polymer of this step being from 80 to 20% by weight of said polypropylene.

5 In step (a) a very high molecular weight random copolymer of propylene and ethylene is prepared, which gives the polypropylene its extremely high shape-resistance. In step (b), essentially homopolymeric low molecular weight polypropylene is prepared, which gives the product good melt-processing properties and improved stiffness.

10 In the process of the invention the order of steps (a) and (b) can freely be chosen. According to one embodiment, step (a) is performed before step (b). According to another embodiment, step (b) is performed prior to step (a). When the low molecular weight PP homopolymer fraction is made in the first reactor and the high molecular weight random copolymer is made in the second reactor, (b) → (a), it gives certain advantages:

- 15 - In most cases it is easier to separate hydrogen than ethylene from the reaction mixture between the reactors.
- When ethylene is fed to the second reactor it increases the activity of the catalyst, which can be particularly important if the second reactor is a gas phase reactor.
- 20 - This order of polymerisation stages also ensure that there is no ethylene in the PP homopolymer, if that is wanted.
- It is easier to produce high comonomer content PP random copolymer. Typically more than 5% ethylene containing PP random copolymer is difficult to produce in loop.

25 Circulation of the hydrogen in the back of the reactor is easier if the step (b) is made in gas phase reactor.

30 Although different catalyst systems of the above mentioned type can be used in steps (a) and (b), it is preferable to use the same catalyst system for both steps. According to a preferable embodiment, the catalyst system is added to step (a) and the same catalyst system is then used both in step (a) and (b).

35 Steps (a) and (b) can be performed in reactors, which may be of any type conventionally used for propylene polymerization and copolymerization, preferentially a loop (CSTR) or gas phase reactor, but it is most preferable to perform one of steps (a) and (b) in a loop (CSTR) reactor and the other step in a gas phase reactor, whereby any reaction medium used and unreactive reagents are removed at least

partly between step (a) and step (b). In such a case the procatalyst (also called catalyst in the art), cocatalyst and external donor are fed to the loop reactor. An advantage of loop gas phase combination compared to two gas phase reactors in series is the flexibility of grade transfer transitions due to shorter residence time of loop reactor. An advantage of loop gas phase combination compared to two loop reactors in series is that in many cases of this invention either unreacted ethylene or hydrogen should be removed between the stages. This is typically made by evaporation the whole reaction medium and at least partial separation of gases and polymer particles, which is not feasible if both stages (a) and (b) are made in loop reactors. The reaction medium and unreacted reagents such as H₂ or comonomer can be removed by known methods between the steps.

It is also preferable to adjust the proportion of copolymer resulting from step (a) and the used melt flow (MFR) of step (a) and step (b) so that the FRR value (MFR₁₀/MFR₂), which is also a measure of the molecular weight distribution, of said polypropylene is between 10 and 100, most preferably between 20 and 50.

The catalyst used in the present process for the preparation of polypropylene can be any suitable catalyst, which consists of a procatalyst, which is a reaction product of at least tetravalent titanium compound and a magnesium halide compound, and a cocatalyst, which comprises an organoaluminium compound, an optionally external electron donor compound.

Preferentially, said catalyst system has been prepared by:

- (i) providing a procatalyst by reacting a magnesium halide compound, chosen from magnesium chloride, its complex with ethanol and other derivatives of magnesium chloride, with titanium tetrachloride and optionally with an internal donor, exemplified by the dialkyl phthalates ,
- (ii) providing as cocatalyst an organoaluminium compound chosen from trialkyl aluminium exemplified by triethyl aluminium, dialkyl aluminium chloride, alkyl aluminium sesquichloride, optionally
- (iii) providing as at least one external donor an ester of an aromatic acid exemplified by methyl p-methyl benzoate, or an organosilicon compound exemplified by alkoxy silanes or blends thereof, and, optionally
- (iv) prepolymerizing a small amount of olefin by contacting the olefin with said procatalyst, cocatalyst and, optionally, the external donor.

In step (a) of the present process, a portion of ethylene is preferably used, which leads to 1.0 to 7.0% by weight of ethylene units in the random copolymer resulting from this step. Further in step (a) preferably no or a minimal amount of hydrogen is used, which leads to a MFR_{10} value of between 0.05 and 2.0 g/min for the random copolymer resulting from this step, if the step is performed first. Also, the proportion of random copolymer resulting from step (a) is preferably from 40 to 80% by weight of said polypropylene. Thus it can be said, that the polypropylene prepared by the process of the invention contains preferably more random copolymer than low molecular weight homopolymer or minirandom copolymer.

10

In step (b), low molecular weight essentially homopolymeric propylene is produced. The molecular weight is adjusted by means of hydrogen. If the hydrogen amount is too high, the molecular weight will be too low and the product will be useless as pipe, profile or moulding material. In step (b) an amount of hydrogen is preferably used, which leads to a MFR_2 value of between 30 and 500 g/10 min for the polymer resulting from this step, if it performed first.

15

As it was said before, too much ethylene units in the low molecular weight component leads to difficulties in retaining good stiffness properties of the product. Thus, in step (b) no or a minimal amount of ethylene is used, which preferably leads to 0.0 to 0.5% by weight of ethylene repeating units in the polymer resulting from this step. Preferably, the low molecular weight homopolymer fraction is smaller than the high molecular weight random copolymer fraction, i.e. the proportion of polymer resulting from step (b) is from 60 to 20% by weight of said polypropylene.

20

According to another embodiment of the present invention, the invention relates to a process for the preparation of elastomer modified polypropylene for e.g. pipe, fiber, film, foam, profile and moulding applications. Such a grade of polypropylene has from 1.0 to 30% by weight of ethylene or a C_4-C_{10} - α -olefin repeating units and has a MFR_2 value of between 0.05 and 50 g/10 min. The preparation takes place by polymerizing propylene and ethylene or a C_4-C_{10} - α -olefin in the presence of a catalyst system, the procatalyst component of which is a reaction product of at least a tetravalent titanium compound and a magnesium halide compound, and a cocatalyst component of which comprises an organoaluminium compound, and hydrogen as a molecular weight regulating agent, as well as providing an elastomer component.

30

35

It has been found that extremely creep-resistant polypropylene can be prepared by applying the following steps:

- 5 (a) copolymerizing propylene and ethylene into a random copolymer at 40 to 110°C using: a catalyst system of the above-mentioned type; a portion of ethylene or C₄-C₁₀- α -olefin leading to 1.0 to 10.0% by weight of ethylene or C₄-C₁₀- α -olefin repeating units in said random copolymer; and no or a minimal amount of hydrogen leading to a MFR₁₀ value of between 0.01 and 5.0 g/10 min for said random copolymer, if this step is performed first, or to a MFR₂ value for said polypropylene of between 0.05 and 50 g/10 min, if this step is performed after step (b);
10 the proportion of random copolymer of this step being from 20 to 80% by weight of said polypropylene,
- (b) polymerizing propylene at 40 to 110°C using: a catalyst system of the above-mentioned type; no or a minimal portion of ethylene leading to 0.0 to 1.0% by weight of ethylene repeating units in the polymer resulting from this step; and an
15 amount of hydrogen leading to a MFR₂ value of between 20 and 1000 g/10 min for said polymer, if this step is performed first, or to a MFR₂ value for said polypropylene of between 0.05 and 50 g/10 min, if this step is performed after step (a); the proportion of polymer of this step being from 80 to 20% by weight of said polypropylene, and
- 20 (c) providing a rubbery copolymer (elastomer) the proportion of which is from 5 to 40% by weight of said polypropylene.

25 In step (a) a very high molecular weight random copolymer of propylene and ethylene is prepared, which gives the polypropylene its extremely high shape-resistance. In step (b), essentially homopolymeric low molecular weight polypropylene is prepared, which gives the product good melt-processing properties and improved stiffness. In step (c), the provided rubbery copolymer gives better impact resistance.

30 In the process of the invention the order of steps (a) and (b) can freely be chosen. It is, however, preferable to perform step (a) before step (b). Although different catalyst systems of the above mentioned type can be used in steps (a) and (b), it is preferable to use the same catalyst system for both steps. According to a preferable embodiment, the catalyst system is added to step (a) and the same catalyst system is
35 then used both in step (a) and (b).

Steps (a) and (b) can be performed in reactors, which may be of any type conventionally used for propylene polymerization and copolymerization preferentially a

loop (CSTR) or gas phase reactor, but it is most preferable to perform one of steps (a) and (b) in a loop (CSTR) reactor and the other step in a gas phase reactor, whereby any reaction medium used and unreactive reagents are removed at least partly between step (a) and step (b). In such a case the procatalyst (also called
5 catalyst in the art), cocatalyst and external donor is fed to the loop reactor. The reaction medium and unreacted reagents such as H₂ or comonomer can be removed by known methods between the steps.

Preferably, steps (a) and (b) are performed so that said polypropylene has a MFR₂
10 value of between 0.1 and 12 g/10 min.

It is also preferable to adjust the proportion of copolymer resulting from step (a) and the used melt flow (MFR) of step (a) and step (b) so that the FRR value (MFR₁₀/MFR₂), which is also a measure of the molecular weight distribution, of
15 said polypropylene is between 10 and 100, most preferably between 20 and 50.

The catalyst used in the present process for the preparation of polypropylene can be any suitable catalyst, which consists of a procatalyst, which is a reaction product of at least tetravalent titanium compound and a magnesium halide compound, and a
20 cocatalyst, which comprises an organoaluminium compound, an optionally external electron donor compound.

Preferentially, said catalyst system has been prepared by:

- (i) providing a procatalyst by reacting a magnesium halide compound, chosen
25 from magnesium chloride, its complex with ethanol and other derivatives of magnesium chloride, with titanium tetrachloride and optionally with an internal donor, exemplified by the dialkyl phthalates,
- (ii) providing as cocatalyst an organoaluminium compound chosen from trialkyl aluminium exemplified by triethyl aluminium, dialkyl aluminium chloride, alkyl
30 aluminium sesquichloride, optionally
- (iii) providing as at least one external donor an ester of an aromatic acid exemplified by methyl p-methyl benzoate, or an organosilicon compound exemplified by alkoxy silanes or blends thereof, and, optionally
- (iv) prepolymerizing a small amount of olefin by contacting the olefin with said
35 procatalyst, cocatalyst and, optionally, the external donor.

In step (a) of the present process, a portion of ethylene or a C₄-C₁₀- α -olefin is preferably used, which leads to 1.0 to 7.0% by weight of ethylene or a C₄-C₁₀- α -

olefin units in the random copolymer resulting from this step. Further in step (a) preferably no or a minimal amount of hydrogen is used, which leads to a MFR₁₀ value of between 0.05 and 2.0 g/min for the random copolymer resulting from this step, if the step is performed first. Also, the proportion of random copolymer
5 resulting from step (a) is preferably from 40 to 80% by weight of said polypropylene. Thus it can be said, that the polypropylene prepared by the process of the invention contains preferably more random copolymer than low molecular weight homopolymer or minirandom copolymer.

10 In step (b), low molecular weight essentially homopolymeric or minirandom (having little comonomer) propylene is produced. The molecular weight is adjusted by means of hydrogen. If the hydrogen amount is too high, the molecular weight will be too low and the product will be useless as pipe, profile or moulding material. In
15 step (b) an amount of hydrogen is preferably used, which leads to a MFR₂ value of between 30 and 500 g/10 min for the polymer resulting from this step, if it performed first.

As it was said before, too much ethylene units in the low molecular weight component leads to difficulties in retaining the stiffness properties of the product. Thus, in step (b) no or a minimal amount of ethylene is used, which preferably leads
20 to 0.0 to 0.5% by weight of ethylene repeating units in the polymer resulting from this step. Preferably, the low molecular weight homopolymer fraction is smaller than the high molecular weight random copolymer fraction, i.e. the proportion of polymer resulting from step (b) is from 60 to 20% by weight of said polypropylene.

25 The step (c) of providing an elastomer preferably follows steps (a) and (b) and, most preferentially, the order of steps is (a) \Rightarrow (b) \Rightarrow (c).

The step (c) of providing an elastomer can be performed in two ways. According to the first and more preferable way, said elastomer is provided by copolymerizing at least propylene and ethylene into an elastomer. The conditions for the
30 copolymerization are within the limits of conventional EPM production conditions such as they are disclosed e.g. in Encyclopedia of Polymer Science and Engineering, Second Edition, Vol. 6, p. 545-558. A rubbery product is formed if the ethylene repeating unit content in the polymer is within a certain interval. Thus, preferentially, in step (c), ethylene and propylene are copolymerized into an
35 elastomer in such a ratio that the copolymer step (c) contains from 10 to 70% by

weight of ethylene units. Most preferably, the ethylene unit content is from 30 to 50% by weight of the copolymeric propylene/ethylene elastomer.

According to preferable embodiments of the invention, the following conditions are independently chosen for the three step process:

- a temperature in step (c) of between 40 and 90°C,
- said catalyst system is added to step (a) and used in both steps (a), (b) and (c),
- step (a) is performed in a loop (CSTR) reactor and steps (b) and (c) are performed in two separate gas phase reactors,
- the added comonomer portion is adjusted so that the proportion of ethylene repeating units after steps (a) and (b) is from 1 to 4% by weight and the proportion of ethylene repeating units after steps (a), (b) and (c) is from 5 to 15% by weight,
- in step (c), ethylene and propylene are copolymerized into an elastomer in a molar ratio ethylene/propylene of between 30/70-50/50.

15

According to another embodiment of the claimed process, the elastomer in step (c) is provided by adding a ready-made or natural elastomer to the reaction product of steps (a) and (b), most preferably an impact modified heterophasic polypropylene having from 15 to 50% by weight of a propylene-ethylene elastomeric copolymer.

20

As polypropylene for pipe, profile and moulding applications has not before been prepared with such a good shape preservice, the invention also relates to an extremely creep-resistant polypropylene for said applications. The creep resistance can be measured by registering the deflection of the material during 500-1000 h using 7.3 or 6.5 MPa load at 60°C. This new material shows a creep level of 1/5 to 1/2 of regular PP (pipe grade) material comparable to e.g. the PP material of comparative example 9. This is a sensational result and can open new application in e.g. piping.

According to one embodiment of the invention, the creep-resistant polypropylene has been made according to the above described process for its preparation. According to another embodiment of the invention, the use of the above mentioned polypropylene is claimed, which use is directed to pipes, profiles, moulded articles and foams, fibres and films.

In addition to ethylene and propylene, the process and the polypropylene according to the invention can contain from 0.0 to 10.0% by weight of any other olefin such as

butene-1, 4-methyl-pentene-1, hexene-1, octene-1 and decene-1 or combinations of them.

5 The stiffness of this material is higher than that for materials produced with about the same comonomer content in several reactors or in only one reactor without losing the impact. That is seen best when comparing the embodiment examples 1 to 10 with comparative examples 1 to 3 which are produced in the same conditions but with different ethylene feed splits. The entanglements and tie-chains of the high molecular fraction in the material give the material better pipe properties especially
10 higher tensile strength tensile modulus charpy impact strength, and lower creep under load. The invented copolymers give also longer time to failure at same hoop stress levels in standard pipe pressure tests than the conventionally produced random pipe material.

15 The invention is in the following illuminated by the following examples and comparative examples.

Examples

The following tests and preparations were made:

Mechanical tests from 4 mm compression moulded plaques. The specimens were according to ISO 527.

20 Tensile strength according to ISO 527 (cross head speed = 50 mm/min).

Tensile modules according to ISO 527 (cross head speed = 1 mm/min).

Charpy, notched impact according to ISO 179/1eA.

Creep test is a Borealis tensile creep method for ranking of pipe materials. In the method a constant stress is applied to a specimen (a modified ISO dumb bell = 120
25 mm long, thickness = 2 mm). The test temperature = 60°C (oven) and the stress = 6.5 or 7.3 mPa (for PP materials).

The increase of strain with time is recorded 500 to 1000 h.

The creep is defined as the elongation at 100 h in mm units corresponding to stiffness and the slope between 100 h and 400 h in angle units.

30 This creep resistance test method is comparable to e.g. ISO 899-1, DIN 53444 and ASTM 2990.

Example 1

Preparation and properties of high MW very broad MWD two-stage random homo-PP copolymer

5

The PP copolymers were produced in a pilot plant having a loop reactor and a fluid bed gas phase reactor connected in series. The catalyst, cocatalyst and donor were fed to the loop reactor. The reaction medium of loop was flashed away before the solid polymer containing the active catalyst entered to the gas phase.

10

The prepolymerized MgCl_2 -supported Ti catalyst (prepared according to patent US 5,234,879, included by reference) was used in the polymerization. Cocatalyst was triethyl aluminium (TEA) and external donor dicyclopentanedimethoxysilane (DCPDMS). Al/Ti mole ratio was 150 and Al/donor mole ratio 5.

15

In the first stage (loop reactor) was produced high MW propylene-ethylene random copolymer, and the polymerization was continued in the second stage (gas phase reactor) which produced low MW homo-PP. The polymerization temperature used in both stages was 70°C . The production rate was 6 kg/h for the first stage and 4 kg/h for the second stage, which means a production split of 60/40. The MFR:s of the first stage and final product were adjusted with separate hydrogen feeds.

20

More detailed properties of the material produced in each stage are shown in Table 1.

25

Example 2

Preparation and properties of moderately broad MWD two-stage random homo-PP copolymer

30

The polymer was polymerized as in example 1, except that the production split was 80/20 and the MW of the random PP produced in the first stage was adjusted slightly lower with hydrogen feed. More detailed properties of the material produced in each stage are shown in Table 1.

35

Example 3

Preparation and properties of very broad MWD two-stage random minirandom-PP copolymer

5

The polymer was polymerized as in Example 1, except that the production split was 61/39, and instead of homo-PP the second stage produced propylene-ethylene random copolymer containing 0.5 w-% ethylene. More detailed properties of the material produced in each stage are shown in Table 1.

10

Example 4

Preparation and properties of broad MWD two stage homo-random-PP copolymer

15

The polymer was polymerized as in Example 1, except that the first stage (loop reactor) produced low MW homo-PP and the second stage high MW propylene-ethylene random copolymer containing about 4 w-% ethylene. The production split was 41/59. More detailed properties of the material produced in each stage are shown in Table 1.

20

Example 5

Preparation and properties of moderately broad MWD two-stage random homo-PP copolymer with another catalyst and higher ethylene content random-PP

25

The polymer was polymerized as in Example 1, except that the catalyst was prepared according to patent US 4,784,983, included by reference, and the high MW random-PP produced in the first stage had higher ethylene content and slightly lower MW. More detailed properties of the material produced in each stage are shown in Table 1.

30

Example 6

Preparation and properties of medium broad MWD two-stage random homo-PP copolymer

35

The polymer was polymerized as in Example 1, except that the production split was 59/41, the MW of the random-PP produced in the first stage was adjusted slightly

lower and that as external donor, cyclohexyl methyl dimethoxy silane was used. More detailed properties of the material produced in each stage are shown in Table 1.

5 **Example 7**

Preparation and properties of moderately broad MWD two-stage random homo-PP copolymer with a higher amount of the homopolymer produced

- 10 The polymer was polymerized as in Example 1, except that the production split was 42/58. More detailed properties of the material produced in each stage are shown in Table 1.

15 **Example 8**

Preparation and properties of moderately broad MWD two-stage random homo-PP copolymer with a lower ethylene content random PP copolymer

- 20 The polymer was polymerized as in Example 1, except that the high MW random PP produced in the first stage had lower ethylene content and the production split was 50/50. More detailed properties of the material produced in each stage are shown in Table 1.

25 **Example 9**

Preparation and properties of broad MWD two-stage homo-random PP copolymer

- 30 The polymer was polymerized as in Example 1, except that the first stage (loop reactor) produced low MW homo-PP and the second stage high MW propylene-1-butene-ethylene random copolymer containing about 1.1 w-% 1-butene and 0.6 w-% ethylene. The production split was 50/50. More detailed properties of the material produced in each stage are shown in Table 1.

35 **Example 10**

Preparation and properties of broad MWD three-stage impact modified random homo-PP copolymer

The PP copolymers were produced in a pilot plant having a loop reactor and two fluid bed gas phase reactors connected in series. The catalyst, cocatalyst and donor were fed to the loop reactor. The reaction medium of loop was flashed away before the solid polymer containing the active catalyst entered to the first gas phase.

5

The prepolymerized MgCl_2 -supported Ti catalyst (prepared according to patent US 5,234,879, included by reference) was used in the polymerization. Cocatalyst was triethyl aluminium (TEA) and external donor cyclohexyl methyl dimethoxy silane.

- 10 In the first stage (loop reactor) was produced high MW propylene-ethylene random copolymer. The polymerization was continued in the second stage (gas phase reactor) which produced low MW homo-PP, and the third stage (gas phase) produced rubbery ethylene-propylene copolymer. The ethylene/propylene mole ratio in the third stage was 30/70. The production split of the stages in weight
15 fractions was 57/26/17. The polymerization temperature used in all stages was 70°C. The MFR:s measured after the polymerization stages were adjusted with separate hydrogen feeds.

20

More detailed properties of the material produced in each stage are shown in Table 2.

Example 11

- Preparation and properties of broad MWD three-stage impact modified random homo-PP copolymer having smaller fraction of homo-PP and larger fraction of
25 rubbery copolymer

- The polymer was polymerized as in Example 7, except that the production split was 63/12/25 and the MW of the random-PP produced in the loop reactor was adjusted lower with small hydrogen feed. The ethylene/propylene mole ratio in the third
30 stage was 36/64. More detailed properties of the material produced in each stage are shown in Table 2.

Example 12

- 35 Preparation and properties of broad MWD three-stage impact modified random-PP copolymer, with low ethylene random-PP made in the second stage

The polymer was polymerized as in Example 8, except that the production split was 58/29/13, and instead of homo-PP the second stage produced low MW propylene-ethylene random copolymer containing 0.5 w-% ethylene. More detailed properties of the material produced in each stage are shown in Table 2.

5

Example 13

Preparation and properties of broad MWD three-stage impact modified homo-random-PP copolymer

10

The polymer was polymerized as in Example 9, except that the first stage (loop reactor) produced low MW homo-PP and the second stage (gas phase reactor) produced high MW propylene-ethylene random copolymer containing about 4 w-% ethylene, and the third stage (gas phase reactor) produced rubbery ethylene-propylene copolymer. The ethylene/propylene mole ratio in the third stage was 33/67. The production split was 36/48/15. As an external donor, dicyclopentane-dimethoxysilane (DCPDMS) was used. More detailed properties of the material produced in each stage are shown in Table 2.

20 Example 14

Preparation and properties of broad MWD two-stage random homo-PP copolymer which is impact modified with melt blended PP block copolymer

25 The polymer composition is a melt blended mixture of 67 w-% of PP random copolymer made according to example 2 and 33 w-% of a impactmodified hetero-phasic PP (MFR2 1.5 g/10 min) having 15 w-% of rubbery propylene-ethylene copolymer. More detailed properties of the material produced in each stage are shown in Table 2.

30

Comparative example 1

Preparation and properties of moderately broad MWD two-stage random-PP copolymer with higher ethylene content of the low MW phase

35

The polymer was polymerized as in Example 3, except that the ethylene content of the low MW polymer produced in the second stage was higher, and the MW of the polymer produced in the first stage was slightly lower. The external donor was

cyclohexylmethyl dimethoxysilane. The production split was 60/40. More detailed properties of the material produced in each stage are shown in Table 1.

Comparative example 2

5

The following material was tested: Borealis commercial PP-pipe grade, RA130E, which is used for hot water pressure pipes.

Comparative example 3

10

Preparation and properties of impact modified low ethylene random-PP copolymer

The PP copolymers were produced in a pilot plant having a loop reactor and a fluid bed gas phase reactor connected in series. The catalyst, cocatalyst and donor were fed to the loop reactor. The reaction medium of loop was flashed away before the solid polymer containing the active catalyst entered to the gas phase. The polymerization temperature used in both reactors was 70°C.

The prepolymerized MgCl_2 -supported Ti catalyst (prepared according to patent US 5,234,879, included by reference) was used in the polymerization. Cocatalyst was triethyl aluminium (TEA) and external donor dicyclopentanedimethoxysilane (DCPDMS).

In the first stage (loop reactor) was produced propylene-ethylene random copolymer of 4% ethylene, and the polymerization was continued in the second stage (gas phase reactor) which produced rubbery propylene-ethylene copolymer. The ethylene/propylene mole ratio in the third stage was 35/65. The production rate in the first stage was 11 kg/h and in the second stage 2.1 kg/h, which means a production split of 84/16. The MFR:s of the first stage and final product were adjusted with separate hydrogen feeds.

More detailed properties of the material produced in each stage are shown in Table 2.

Comparative example 4

35

Preparation and properties of impact-modified propylene-ethylene random copolymer with higher MW of the rubbery phase

The polymer was polymerized as in comparative Example 3, except that the rubbery propylene-ethylene copolymer was produced without any hydrogen feed to the gas phase reactor. More detailed properties of the material produced in each stage are shown in Table 2.

TABLE 1: RANDOM HOMO PP COPOLYMERS for pipe (homo random PP copolymers)

	Ex. 1	Ex. 2	Ex. 3	Ex. 4	Ex. 5	Ex. 6	Ex. 7	Ex. 8	Ex. 9	Comp. 1	Comp. 2
MFR, 2.16 kg	0.14	0.18	0.16	0.15	0.19	0.29	0.2	0.2	0.5	0.15	0.18
MFR, 10 kg	7	4	6.9	5.6	4.5	8.7	5.3		10.4	4.7	
FRR, 10/2.16	50	22.2	43.1	37.1	23.9	30	26.5		20.8	31.3	
FINAL ETHENE											
1. stage, ethene	1.8	3	2.6	2.7	2.9	2.3	1.6	1.35	0.6	3.4	3.6
final butene	4	4	3.9	0	5.8	3.9	4	2	0	4	4
									1.1		
Melting peak, Tm	161.2	161.3	149	161.4/154.4	159.7	155.1/160.9	159.6	157.3	160.6	147.2	141.9
Tensile strength	30	25.4	28.1	27.9	27.6	27.5	30.6	34	35.6	23.9	22.2
elongation at yield	8.7	10.5	10.8	9.7	9.4	10	9.4	9	7.3	14.5	12.3
Tensile modulus	1320	1010	1140	1110	1080	970	1360	1520	1730	870	790
Charpy, notched, RT	6.4	10.1	5.8	8.1	8.3	10.7	9.3	4.6	2.3	40	11.3
Charpy, notched, 0°C	2.1	2.6	2	2.3	2	3.1	21.7			2.2	2
Creep at 60°C, 7.3 MPa											
displacement at 100h/slope	0.6/0.74	0.6/1.0	1.0/1.0	0.9/0.6	1.1/0.6	1.1/0.66	0.9/0.62	0.8/0.54	0.4/0.4	2.2/2.0	2.6/2.0
1. stage, MFR, 10 kg, a→b	0.09	0.94	0.19	-	0.3	1.7	0.17	0.23	21	0.2	0.9
1. stage, MFR, 2.16 kg, b→a				105							
Production split	60/40	80/20	61/39	41/59	60/40	59/41	42/58	50/50	50/50	60/40	60/40

TABLE 2
IMPACT MODIFIED RANDOM HOMO PP COPOLYMERS
 (impact modified homo random PP co)

		Ex. 10	Ex. 11	Ex. 12	Ex. 13	Ex. 14	Comp. 3	Comp. 4
MFR, 2.16 kg	g/10'	0.13	0.14	0.19	0.16	0.4	0.2	0.18
MFR, 10 kg	g/10'	3.6	3.7	5.7	5.8	9.9	3.3	3.1
FRR, 10/2.16		27.4	26.4	30	36	24.7	16.6	17.4
FINAL ETHENE	w-%	4.9	6.8	6.8	7.5		6.9	7.7
2. stage, ethene	w-%	1.5	1.7	1.8	2.8		-	-
1. stage, ethene	w-%	3.2	3.5	3.2	0		0.8	0.8
Melting peak, Tm	°C	154.7	154.6	150.9	158		155.7	155.3
Tensile strength	MPa	23.3	21.3	21.7	20.5	26.1	22.7	20.7
elongation at yield	%	9.8	9.2	10.5	7.5	9.1	7.8	7.7
Tensile modulus	MPa	940	860	860	880	1070	1010	960
Charpy, notched, RT	kJ/m ²	53	69	66	56	24	55	54
Charpy, notched, 0°C	kJ/m ²	6	18.1	6.9	11.2	3.9	24.2	13.4
Charpy, notched, -20°C	kJ/m ²	2.3	3.7	3.4	5.2	-	7.5	8.1
Creep at 60°C, 7.3 MPa								
displacement at 100h/slope	mm/deg	2.5/2.3	3.2/5.1	4.0/8.0	-	1.5/1.1	2.2/4.4	6/-
creep at 60°C, 6.5 MPa	mm/deg				2.2/3.1			-
Extrudability		good	good	good	good	-	bad	severe
1. stage, MFR, 2.16 kg, b→a	g/10'	-	-	-	90	-	0.2	0.27
1. stage, MFR, 10 kg, a→b	g/10'	0.7	0.7	0.7	-			
2. stage, MFR, 2.16 kg	g/10'	0.1	0.2	0.3	0.45		-	-
Production split	%/%	58/26/16	63/12/25	58/29/13	36/48/15	53/42/5	84/16	84/16

Claims

1. A process for the preparation of polypropylene for e.g. pipe, fiber, profile and moulding applications, containing from 1.0 to 10.0% by weight of ethylene or C₄-C₁₀- α -olefin repeating units and having a MFR₂ value of between 0.05 and 0.40 g/10 min, by polymerizing propylene and ethylene or a C₄-C₁₀- α -olefin in the presence of a catalyst system, the procatalyst component of which is a reaction product of at least a tetravalent titanium compound and a magnesium halide compound and the cocatalyst component of which comprises an organoaluminium compound, optionally an external donor and hydrogen as a molecular weight regulating agent, to give said polypropylene, characterized in that it is a process for the preparation of creep-resistant polypropylene which comprises the following steps in any mutual order:

(a) copolymerizing propylene and ethylene or a C₄-C₁₀- α -olefin into a random copolymer at 40 to 110°C using: a catalyst system of the above-mentioned type; a portion of ethylene or C₄-C₁₀- α -olefin leading to 1.0 to 10.0% by weight of ethylene or C₄-C₁₀- α -olefin repeating units in said random copolymer; and no or a minimal amount of hydrogen leading to a MFR₁₀ value of between 0.01 and 5.0 g/10 min for said random copolymer, if this step is performed first, or to a MFR₂ value for said polypropylene of between 0.05 and 0.40 g/10 min, if this step is performed after step (b); the proportion of random copolymer of this step being from 20 to 80% by weight of said polypropylene,

(b) polymerizing propylene at 40 to 110°C using: a catalyst system of the above-mentioned type; no or a minimal portion of ethylene leading to 0.0 to 1.0% by weight of ethylene repeating units in the polymer resulting from this step; and an amount of hydrogen leading to a MFR₂ value of between 20 and 1000 g/10 min for said polymer, if this step is performed first, or to a MFR₂ value for said polypropylene of between 0.05 and 0.40 g/10 min, if this step is performed after step (a); the proportion of polymer of this step being from 80 to 20% by weight of said polypropylene.

30

2. Process according to Claim 1, characterized in that the order of steps is (a) \Rightarrow (b).

3. Process according to Claim 2, characterized in that said catalyst system is added to step (a) and the same catalyst system is then used both in step (a) and (b).

35

4. Process according to Claim 1, characterized in that the order of steps is (b) \Rightarrow (a).
5. Process according to Claim 4, characterized in that said catalyst system is added to step (b) and the same catalyst system is used both in step (b) and (a).
- 5 6. Process according to any preceding Claim, characterized in that step (a) is performed in a loop (CSTR) reactor and step (b) is performed in a gas phase reactor, whereby any reaction medium used and any unreacted reagents are removed at least partly between step (a) and step (b).
- 10 7. Process according to any preceding claim, characterized in that the proportion of copolymer resulting from step (a) and the MFR values of step (a) and step (b) are such that the FRR value ($= \text{MFR}_{10}/\text{MFR}_2$) of said polypropylene is between 10 and 100, preferentially between 20 and 50.
- 15 8. Process according to any preceding claim, characterized in that said catalyst system has been prepared by:
- (i) providing a procatalyst by reacting a magnesium halide compound, chosen from magnesium chloride, its complex with ethanol and other derivatives of magnesium chloride, with titanium tetrachloride and optionally with an internal
- 20 donor, exemplified by the dialkyl phthalates,
- (ii) providing as cocatalyst an organoaluminium compound chosen from trialkyl aluminium exemplified by triethyl aluminium, dialkyl aluminium chloride, alkyl aluminium sesquichloride, optionally
- (iii) providing as at least one external donor an ester of an aromatic acid exemplified by methyl p-methyl benzoate, or an organosilicon compound exemplified by
- 25 alkoxy silanes or blends thereof, and, optionally
- (iv) prepolymerizing a small amount of olefin by contacting the olefin with said procatalyst, cocatalyst and, optionally, the external donor.
- 30 9. Process according to any preceding claim, characterized in that in step (a), a portion of ethylene is used, which leads to 1.0 to 7.0% by weight of ethylene units in the random copolymer resulting from this step.
10. Process according to any preceding claim, characterized in that in step (a), no
- 35 or a minimal amount of hydrogen is used, which leads to a MFR_{10} value of

between 0.05 and 2.0 g/10 min for the random copolymer resulting from this step, if the step is performed first.

11. Process according to any preceding claim, characterized in that the proportion of random copolymer resulting from step (a) is from 40 to 80% by weight of said polypropylene.

12. Process according to any preceding claim, characterized in that in step (b), no or a minimal amount of ethylene is used, which leads to 0.0 to 0.5% by weight of ethylene repeating units in the polymer resulting from this step.

13. Process according to any preceding claim, characterized in that in step (b), an amount of hydrogen is used, which leads to a MFR₂ value of between 30 and 500 g/10 min for the polymer resulting from this step, if it is performed first.

14. Process according to any preceding claim, characterized in that the proportion of polymer resulting from step (b) is from 60 to 20% by weight of said polypropylene.

15. A process for the preparation of elastomer modified polypropylene for e.g. pipe, fiber, film, profile and moulding applications, containing from 1.0 to 30% by weight of ethylene or C₄-C₁₀- α -olefin repeating units and having a MFR₂ value of between 0.05 and 50 g/10 min, by polymerizing propylene and ethylene or a C₄-C₁₀- α -olefin in the presence of a catalyst system, the procatalyst component of which is a reaction product of at least a tetravalent titanium compound and a magnesium halide compound and the cocatalyst component of which comprises an organoaluminium compound, and hydrogen as a molecular weight regulating agent, as well as providing an elastomer component, to give said elastomer modified polypropylene, characterized in that it is a process for the preparation of creep-resistant and stiff polypropylene which comprises the following steps:

(a) copolymerizing propylene and ethylene or a C₄-C₁₀- α -olefin into a random copolymer at 40 to 110°C using: a catalyst system of the above-mentioned type; a portion of ethylene or C₄-C₁₀- α -olefin leading to 1.0 to 10.0% by weight of ethylene or C₄-C₁₀- α -olefin repeating units in said random copolymer; and no or a minimal amount of hydrogen leading to a MFR₁₀ value of between 0.01 and 5.0 g/10 min for said random copolymer, if this step is performed first, or to a MFR₂ value for said polypropylene of between 0.05 and 50 g/10 min, if this step is

performed after step (b); the proportion of random copolymer of this step being from 20 to 80% by weight of said polypropylene,

- (b) polymerizing propylene at 40 to 110°C using: a catalyst system of the above-mentioned type; no or a minimal portion of ethylene leading to 0.0 to 1.0% by weight of ethylene repeating units in the polymer resulting from this step; and an amount of hydrogen leading to a MFR₂ value of between 20 and 1000 g/10 min for said polymer, if this step is performed first, or to a MFR₂ value for said polypropylene of between 0.05 and 50 g/10 min, if this step is performed after step (a); the proportion of polymer of this step being from 80 to 20% by weight of said polypropylene, and
- (c) providing a rubbery copolymer (elastomer), the proportion of which is from 5 to 40% by weight of said polypropylene, to give said elastomer modified polypropylene.

16. Process according to Claim 15, characterized in that the order of steps (a) and (b) is (a)⇒(b).

17. Process according to Claim 15 or 16, characterized in that said catalyst system is added to step (a) and the same catalyst system is then used both in step (a) and (b).

18. Process according to Claim 15, characterized in that the order of steps (a) and (b) is (b)⇒(a).

19. Process according to Claim 18, characterized in that said catalyst system is added to step (b) and the same catalyst system is used both in step (b) and (a).

20. Process according to any of Claims 15 to 19, characterized in that step (a) is performed in a loop (CSTR) reactor and step (b) is performed in a gas phase reactor, whereby any reaction medium used and any unreacted reagents are removed at least partly between step (a) and step (b).

21. Process according to any of claims 15 to 20, characterized in that the proportion of copolymer resulting from step (a) and the MFR values of step (a) and step (b) are such that the FRR value (= MFR₁₀/MFR₂) of said polypropylene is between 10 and 100, preferentially between 20 and 50.

22. Process according to any of claims 15 to 21, characterized in that said catalyst system has been prepared by:
- (i) providing a procatalyst by reacting a magnesium halide compound, chosen from magnesium chloride, its complex with ethanol and other derivatives of magnesium chloride, with titanium tetrachloride and optionally with an internal donor, exemplified by the dialkyl phthalates,
 - (ii) providing as cocatalyst an organoaluminium compound chosen from trialkyl aluminium exemplified by triethyl aluminium, dialkyl aluminium chloride, alkyl aluminium sesquichloride, optionally
 - (iii) providing as at least one external donor an ester of an aromatic acid exemplified by methyl p-methyl benzoate, or an organosilicon compound exemplified by alkoxy silanes or blends thereof, and, optionally
 - (iv) prepolymerizing a small amount of olefin by contacting the olefin with said procatalyst, cocatalyst and, optionally, the external donor.
23. Process according to any of claims 15 to 22, characterized in that in step (a), a portion of ethylene is used, which leads to 1.0 to 7.0% by weight of ethylene units in the random copolymer resulting from this step.
24. Process according to any of claims 15 to 23, characterized in that in step (a), no or a minimal amount of hydrogen is used, which leads to a MFR₁₀ value of between 0.05 and 2.0 g/10 min for the random copolymer resulting from this step, if the step is performed first.
25. Process according to any of claims 15 to 24, characterized in that the proportion of random copolymer resulting from step (a) is from 40 to 80% by weight of said elastomer modified polypropylene.
26. Process according to any of claims 15 to 25, characterized in that in step (b), no or a minimal amount of ethylene is used, which leads to 0.0 to 0.5% by weight of ethylene repeating units in the polymer resulting from this step.
27. Process according to any of claims 15 to 26, characterized in that in step (b) an amount of hydrogen is used, which leads to a MFR₂ value of between 30 and 500 g/10 min for the polymer resulting from this step, if it is performed first.

28. Process according to any of claims 15 to 27, characterized in that the proportion of polymer resulting from step (b) is from 60 to 20% by weight of said elastomer modified polypropylene.
- 5 29. A process according to any of claims 15 to 28, characterized in that step (c) follows steps (a) and (b), preferably in the order (a) \Rightarrow (b) \Rightarrow (c).
30. A process according to any of claims 15 to 29, characterized in that in step (c), said elastomer is provided by copolymerizing at least propylene and ethylene into an elastomer.
- 10 31. A process according to Claim 30, characterized in that in step (c), ethylene and propylene are copolymerized into an elastomer in such a ratio, that the copolymer of step (c) contains from 10 to 70% by weight of ethylene units.
- 15 32. A process according to Claim 30 or 31, characterized in that the following conditions are independently chosen for the three-step process:
- a temperature in step (c) of between 40 and 90°C,
 - said catalyst system is added to step (a) and used in both steps (a), (b) and (c),
 - step (a) is performed in a loop (CSTR) reactor and steps (b) and (c) are per-

20 formed in two separate gas phase reactors,

 - the added comonomer portion is adjusted so that the proportion of ethylene repeating units after steps (a) and (b) is from 1 to 4% by weight and the proportion of ethylene repeating units after steps (a), (b) and (c) is from 5 to 15% by weight,
 - in step (c), ethylene and propylene are copolymerized into an elastomer in a

25 molar ratio ethylene/propylene of between 30/70-50/50.
33. A process according to any of claims 15 to 29, characterized in that in step (c), the elastomer is provided by adding a ready made or natural elastomer to the reaction product of steps (a) and (b).
- 30 34. A process according to Claim 33, characterized in that in step (c), the added ready made elastomer is an impact modified polyolefin.
- 35 35. A process according to any of claims 15 to 34, characterized in that in step (c) said impact modified polyolefin is an impact-modified heterophasic polypropylene having from 5 to 30% by weight of a propylene-ethylene elastomeric copolymer.

36. Creep-resistant polypropylene for e.g. pipe, profile and moulding applications, characterized in that it shows a creep level of $1/5$ to $1/2$ of regular PP material measured by tensile creep method.
- 5 37. Creep-resistant polypropylene according to Claim 36, characterized in that it has been prepared by a process according to one of claims 1 to 35.
38. The use of a creep resistant polypropylene according to Claim 36 or 37 for pipes, fibre, film, profiles, moulded articles and foams.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/FI 97/00240

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: C08F 297/08

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WPI

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0028076 A1 (MITSUBISHI CHEMICAL INDUSTRIES LIMITED), 6 May 1981 (06.05.81) -----	1-38

☐ Further documents are listed in the continuation of Box C.☒ See patent family annex.

* Special categories of cited documents:

- * "A" document defining the general state of the art which is not considered to be of particular relevance
- * "E" earlier document but published on or after the international filing date
- * "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- * "O" document referring to an oral disclosure, use, exhibition or other means
- * "P" document published prior to the international filing date but later than the priority date claimed

* "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

* "X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

* "Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

* "&" document member of the same patent family

Date of the actual completion of the international search

7 July 1997

Date of mailing of the international search report

28 -07- 1997

Name and mailing address of the ISA/
Swedish Patent Office
Box 5055, S-102 42 STOCKHOLM
Facsimile No. +46 8 666 02 86

Authorized officer

Agneta Österman Wallin
Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT

Information on patent family members

01/07/97

International application No.

PCT/FI 97/00240

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0028076 A1	06/05/81	AU 6197880 A	30/04/81
		JP 1429981 C	09/03/88
		JP 56061415 A	26/05/81
		JP 62039603 B	24/08/87
		US 4339557 A	13/07/82
